


CORK

MRA CORKS


Caliber	All	
Class	All	
Marking	Ink and/or fire	
Packing	Polyethylene bags with So2	
Expedition	Cardboard boxes in plastic pallet	
Intend use	Still wines	

Tests and Units	Specifications / Tolerance	Method
Dimensions and ovality	$L \pm 0,5 \text{ mm} \mid \varnothing: \pm 0,5 \text{ mm} \mid O: \leq 0,5 \text{ mm}$	ISO 9727-1:2007
Specific weight	$290 \pm 40 \text{ Kg/m}^3$	ISO 9727-2:2007
Humidity	6% +/- 2%	ISO 9727-3:2007
Extraction force	12 - 30 daN	ISO 9727-5:2007
Liquid seal	2,5 bar	ISO 9727-6:2007
Peroxide residues	< 0 mg/cork stopper	NP 4502:2010
Sensorial analysis	Without deviations	ISO 22308:2005
2,4,6 - Tricloroanisol (TCA)	$\leq 2 \text{ ng/L}$	ISO 20752:2014

JGR S.A
Rua de S. José, 51
4520-475 Rio Meão - Portugal


Phone: + 351 227 446 605
E.mail: info@jgr.pt

www.jgr.pt



CORK

MRB CORKS

Caliber	All	
Class	All	
Marking	Ink and/or fire	
Packing	Polyethylene bags with So2	
Expedition	Cardboard boxes in plastic pallet	
Intend use	Still wines	

Tests and Units	Specifications / Tolerance	Method
Dimensions and ovality	$L \pm 0,5 \text{ mm} \mid \varnothing: \pm 0,5 \text{ mm} \mid O: \leq 0,5 \text{ mm}$	ISO 9727-1:2007
Specific weight	$290 \pm 40 \text{ Kg/m}^3$	ISO 9727-2:2007
Humidity	6% +/- 2%	ISO 9727-3:2007
Extraction force	12 - 30 daN	ISO 9727-5:2007
Liquid seal	2,5 bar	ISO 9727-6:2007
Peroxide residues	< 0 mg/cork stopper	NP 4502:2010
Sensorial analysis	Without deviations	ISO 22308:2005
2,4,6 - Tricloroanisol (TCA)	$\leq 2 \text{ ng/L}$	ISO 20752:2014

JGR S.A
Rua de S. José, 51
4520-475 Rio Meão - Portugal

Phone: + 351 227 446 605
E.mail: info@jgr.pt

www.jgr.pt